


statex®

BAUR software for the statistical estimation of the cable life time

engineered by 



3D illustration of the correlation between normalised evaluation parameters of dissipation factor measurements MTD, Δ TD and TD-Skirt: The framed area top right in the illustration exhibits a high probability of error.

Experienced-based analysis of the cable condition and estimation of the statistical remaining life time

- Analysis of the entire cable network condition based on different dissipation factor parameters
- LT Wizard – statistical tool for defining parameters for determining the remaining life time
- Innovative, patented evaluation algorithm for the statistical estimation of the remaining life time of MV cables
- Validated by 45,000 dissipation factor measurements on 15,000 cable routes

The statex® analysis software is used for the detailed determination of the ageing condition, the speed of ageing and the statistical remaining life time of a cable route based on the dissipation factor diagnostics with VLF truesinus® voltage (Very Low Frequency).

In addition to the conventional evaluation parameters of IEEE 400.2 (SDTD, MTD and Δ TD), the statex® also takes into account a new parameter - TD-Skirt - which illustrates the time stability of the dissipation factor (TD). This makes it possible to calculate the ageing index R and the speed of ageing V_R of the cable route. It is also possible to receive an exact recommendation for when a subsequent measurement should be performed, or when work is required on the cable route. The economical operating limit of the cable and a company-specific safety margin are also incorporated in the calculation, which determines the optimal point in time to replace the cable.

Taking into consideration individual company guidelines and the visualisation of complex correlations between the various analysis parameters in a 3D matrix, statex® offers a new, ground-breaking option for cost-effective, operationally safe asset management.

Features

- LT Wizard – a comprehensive statistical tool for evaluating measurement results and defining limit values for calculating the remaining life time of various cable types and lengths
- Information on the overall network condition enables targeted responses to critical cable conditions
- Determines the speed of ageing and the remaining life time of a cable based on the dissipation factor diagnostics with VLF truesinus® voltage
- 3D illustration of the correlation between normalised evaluation parameters MTD, Δ TD and TD-Skirt as a basis for determining the remaining life time of the cable
- Takes into consideration company-specific guidelines when determining a point in time for cable repairs (security of supply)
- New evaluation parameter TD-Skirt for estimating the remaining life time
- Ageing index R for the overall assessment of the dielectric losses, and voltage and time stability
- Calculates an "action required" date
- BAUR diagnostics systems deliver measurement data to the required level of precision
- Simple maintenance of measurement and cable data in a central cable database

Objectives


- Optimal estimation of the remaining life time of the cable route
- Reduction in the failure rate
- Prevention of social costs

Estimating the statistical remaining life time (principle)


Based on the statistical evaluation of 45,000 units of measurement data on 15,000 cable routes (approx. 7,000 km), the patented algorithm of the statex® analysis software calculates a 3D ageing index R. This algorithm was developed and patented by the Korea Electric Power Corporation (KEPCO) in collaboration with Mokpo University (Korea).

Apart from the normalised evaluation of MTD and ΔTD, the calculation of the 3D ageing index R also takes into consideration the new evaluation parameter, TD-Skirt. In addition to the parameters MTD, SDTD and ΔTD defined in IEEE 400.2, the calculation of the ageing index R enables a precise recommendation of when a subsequent measurement should take place, or when work is required on the cable route, e.g. in three year's time.

Evaluation according to IEEE 400.2*



Evaluation with statex®



Following on from the subsequent measurement and the recalculation of the ageing index R, and based on the index R of the two measurements, the speed of ageing and the anticipated remaining life time of the cable route are calculated. The difference between the economical operating limit and the specific safety margin of the utility company makes it possible to conclude when work will be required on the cable route.

Example – saving at KEPCO by using statex®

The evaluation of the TD measurement data of the 15,000 cable routes according to IEEE 400.2 determined that approx. 255 km of the cable in operation fell under the "Action required" (🔴) category.

The evaluation of the same measurement data with statex® determined that approx. 55 km of the operational cable had a statistical remaining life time of <2 years. This means that it was not yet necessary to replace approx. 200 km of cable.

The KEPCO investigations showed that, compared with the evaluations performed according to the IEEE criteria, the evaluation of the measurements with statex® showed an average increase of 11 years in the statistical remaining life time of a cable.

Software evaluation options

- Display of the ageing index R for L1, L2, L3 of a cable route
- Historical course of the ageing index in the 3D illustration – compared to 45,000 measurement points of KEPCO
- Results:
 - Ageing index R
 - Speed of ageing V_R
 - Statistical remaining life time
 - Point in time of subsequent measurement
 - Calculated failure date
 - 3D status graph
 - TD-Skirt graph
- Warning notification of a calculated, potential failure
- Reminder function for new subsequent measurements
- Import of BAUR TD measurement data (BMF, MMF, IMF, MHT, CSV)

Company-specific setting options


- Ageing index R for various cable types
- Limit values for the ageing index R
- Safety buffer for cable repair or replacement prior to the calculated end of the duty period
- Definition of company evaluation criteria or criteria according to IEEE 400.2

* Evaluation criteria according to IEEE 400.2:

- 🟢 No action required
- 🟡 Further study advised
- 🔴 Action required

Example – calculating the statistical remaining life time of a cable

In the following example, the statistical start of ageing (DSP – degradation starting point) is assumed to be at 13 years, and the critical cable condition (CP – critical point) a value of 7.0.



An initial dissipation factor measurement after a duty period (DP) of 26 years gives a value for the ageing index R_1 of the cable of 2.0. The speed of ageing V_{R1} can thus be calculated after the first measurement. With the speed of ageing, the statistical remaining life time (RLT) of the cable can be calculated after the first measurement.

$$V_{R1} = \frac{R_1}{DP_1 - DSP} = \frac{2.0}{26 \text{ years} - 13 \text{ years}} = 0.15 \text{ years}^{-1} \quad RLT_1 = \frac{CP - R_1}{V_{R1}} = \frac{7.0 - 2.0}{0.15 \text{ years}^{-1}} = 32.5 \text{ years}$$

From the statistical remaining life time, the anticipated operational age A_{CP1} of the cable when it reaches the critical cable condition can be deduced:

$$A_{CP1} = DP_1 + RLT_1 = 26 \text{ years} + 32.5 \text{ years} = 58.5 \text{ years}$$

Measuring again after 10 years, i.e. when the cable has a duty period of 36 years, gives a second ageing index R_2 with the value 4.5. The speed of ageing V_{R2} , the statistical remaining life time RLT_2 and the anticipated operational age A_{CP2} of the cable when it reaches the critical cable condition can then be calculated as follows:

$$V_{R2} = \frac{R_2 - R_1}{DP_2 - DP_1} = \frac{4.5 - 2.0}{36 \text{ years} - 26 \text{ years}} = 0.25 \text{ years}^{-1} \quad RLT_2 = \frac{CP - R_2}{V_{R2}} = \frac{7.0 - 4.5}{0.25 \text{ years}^{-1}} = 10 \text{ years}$$

$$A_{CP2} = DP_2 + RLT_2 = 36 \text{ years} + 10 \text{ years} = 46 \text{ years}$$

A second remeasurement after 8 years, i.e. when the cable has a duty period of 44 years, gives a third ageing index R_3 with the value 5.7. The speed of ageing V_{R3} , the statistical remaining life time RLT_3 and the anticipated operational age A_{CP3} of the cable when it reaches the critical cable condition can then be calculated as follows:

$$V_{R3} = \frac{R_3 - R_2}{DP_3 - DP_2} = \frac{5.7 - 4.5}{44 \text{ years} - 36 \text{ years}} = 0.15 \text{ years}^{-1} \quad RLT_3 = \frac{CP - R_3}{V_{R3}} = \frac{7.0 - 5.7}{0.15 \text{ years}^{-1}} = 8.7 \text{ years}$$


$$A_{CP3} = DP_3 + RLT_3 = 44 \text{ years} + 8.7 \text{ years} = 52.7 \text{ years}$$

Taking into consideration the specific ageing of the cable, the evaluation of the two remeasurements give a potential duty period of the cable of approx. 52.7 years.

VLF TD criteria

New evaluation parameter TD-Skirt

In cables with insulation losses, there are precursors such as the constant increase or decrease or a fluctuation of TD values within a voltage step. The degree of change is known as TD-Skirt and describes the time stability of TD measurements. This is achieved by drawing a virtual line between the largest and smallest TD values of eight consecutive TD measurements. A linear (rising) trend in the measured values indicates a change in the dielectric losses of the cable insulation, while a falling or non-linear trend indicates e.g. moisture or electrical discharge in the cable terminations or joints.



Ageing index R

The ageing index R is calculated from the normalised values MTD, ΔTD and TD-Skirt, and provides information on the condition of the cable insulation of the cable under test at the time of the measurement. It is presented as a 3D vector.

$$R = \sqrt{MTD_{norm}^2 + \Delta TD_{norm}^2 + TD-Skirt_{norm}^2}$$

Technical data

General		System requirements	
User interface languages	English, German Other languages on request	Operating system	Windows 7 (or higher) Recommended: Windows 8 (or higher)
Data import format	BMF, MMF, IMF, MHT, CSV	Memory	Min. 4 GB RAM Recommended: min. 8 GB RAM
Report export format	PDF, PNG	SQL server	Microsoft SQL Server 2019
		Microsoft .NET Framework	4.5 (or higher)
		Recommended screen resolution	1920 x 1080 pixels (Full HD)

Available software licences

Licences	Functions		
	R calculation	Estimation of the remaining life time	LT Wizard
statex® core	✓	X	X
statex® pro (main licence)	✓	✓	✓
Additional licence for statex® pro (in combination with statex® pro main licence only)	✓	✓ (calculation parameters are set centrally using the LT Wizard of the statex® pro main licence)	X
statex® pro package: 1 main licence + 2 additional licences	✓	✓	✓



Software engineered by KEPCO

Contact:

BAUR GmbH (Headoffice Österreich)
T +43 (0)5522 4941-0
headoffice@baur.at

BAUR Prüf- und Messtechnik GmbH
T +49 (0)2181 2979 0
vertrieb@baur-germany.de

BAUR GmbH (Branch UAE)
T +971 50 4440270
shibu.john@baur.at

BAUR France
T +33 (04) 69 98 27 27
infoFR@baur.eu

Baur do Brasil Ltda.
T +55 11 297 25 272
atendimento@baurdobrasil.com.br

BAUR Test Equipment Ltd. (UK)
T +44 (0)20 8661 0957
sales@baurtest.com

奥地利保尔公司上海代表处
电话 +86 (0)21 6133 1877
shanghaioffice@baur.at

BAUR Representative Office Hong Kong
T +852 2780 9029
office.hongkong@baur.at

BAUR representatives:
www.baur.eu > BAUR worldwide

